

5190243IB02

2020090902



Report No: 2020090902
Applicant: MEDTEX SWISS LTD.
24 Osmi Mart Str. , Gabrovo 5300, Bulgaria
Contact Person: Biser SHARKOV
Contact Telephone: 0212 671 8303
Contact e-mail: sharkov@medhouse.bg
Sample Accepted on: 08.09.2020
Report Date: 09.09.2020
Total number of pages: 9 (Pg)

Sample ID: Three-Layer Disposable Medical Mask

TEST	METHOD	Specimen	RESULT
* Medical face masks - Requirements and test methods	EN 14683+AC 2019	Three-Layer Disposable Medical Mask	PASS
			TYPE IIR



Seal



Customer Representative
Hasan KUTLU



Laboratory Manager
Hava SARIAYDIN

TEST RESULTS**EN 14683 Inspection****SAMPLE : Three-Layer Disposable Medical Mask**

Test	Type			Result	Evaluation	
Bacterial filtration efficiency (BFE), (%)	1 ≥ 95	2 ≥ 98	2R ≥ 98	99,01	98,98	PASS
				99,85		
				99,98		
				98,96		
				99,00		
Differential pressure (Pa/cm ²)	< 40	< 40	< 60	36	PASS	
Splash resistance pressure (kPa)	N/A	N/A	≥ 16,0	18	Type IIR	
Microbial cleanliness (cfu/g)	≤ 30			21	PASS	

Free Area